



Meas-No. 16602 **Name** 210042 (2) **Date** 23-Apr-21 14:02:25
Material cement **Lot** **RMS-Error** 1,07%
Information water **Comment** S210042 **Beam Obscuration** 18%



 16602 dQ3(x) — 16602 Q3(x)

| % | < μm |
|------|------|
| 10,0 | 2,5 |
| 20,0 | 4,3 |
| 30,0 | 6,0 |
| 40,0 | 7,8 |
| 50,0 | 9,9 |
| 60,0 | 12,8 |
| 70,0 | 17,4 |
| 80,0 | 27,3 |
| 90,0 | 55,2 |

| % | < μm |
|------|-------|
| 0,0 | 0,1 |
| 1,7 | 0,5 |
| 3,5 | 1,0 |
| 7,5 | 2,0 |
| 24,2 | 5,0 |
| 50,3 | 10,0 |
| 73,6 | 20,0 |
| 81,6 | 30,0 |
| 85,8 | 40,0 |
| 88,8 | 50,0 |
| 91,0 | 60,0 |
| 92,5 | 70,0 |
| 93,7 | 80,0 |
| 94,5 | 90,0 |
| 95,0 | 100,0 |